


# Technical Data Sheet

## StoCryl GW 100

Impregnation, hydrophobic



### Characteristics

**Area of application** • hydrophobic impregnation for the protection of concrete structures

**Properties**

- reduces the ingress of water and harmful substances dissolved in water
- regulates the moisture balance
- increases electrical resistivity
- good penetration capacity
- very good bond with the substrate and with subsequent intermediate coats and finishes
- water-dilutable

**Appearance** • transparent

**Information/notes**

- product is in accordance with EN 1504-2
- not for surfaces subject to foot or vehicle traffic
- component of the StoCretec system in accordance with the DAfStb (German) Repair Guideline 2001-10
- Surface protection system OS 2 (OS B)

### Technical data

Criterion	Standard / test specification	Value/ Unit	Notes
Density	EN ISO 2811	0.8 - 1.0 g/cm <sup>3</sup>	
The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.			

### Substrate

#### Requirements

Requirements on the substrate:  
The concrete substrate must be load-bearing and free from native and foreign release agents, as well as from corrosion-promoting components (e.g. chlorides). Remove weak layers and laitance.

Dry in accordance with the definition of the DAfStb (German) Repair Guideline 2001-10, but depending on the compressive strength class. Residual moisture may amount to max. 4 wt% for concrete in strength classes up to C30/37 and max. 3 wt% for C35/45 concrete, measured with a calcium carbide meter.

## Technical Data Sheet

### StoCryl GW 100

**Preparations** Prepare the substrate using a suitable mechanical process, such as abrasive blasting or high-pressure water blasting (> 800 bar).  
Open pores and blow-holes sufficiently.

#### Application

**Application temperature** Lowest application temperature: +8 °C  
Highest application temperature: +30 °C

**Mixing ratio** Material in accordance with the description / water = 1.0 : 4.0 parts by weight

**Material preparation** StoCryl GW 100 must be diluted with water.  
Dilution ratio: 1 part by weight of StoCryl GW 100 + 4 parts by weight of water.  
The ready-to-use material must be applied on the same day as it is diluted.

Consumption	Type of application	Approx. consumption	
	concentrate, as a hydrophobic impregnation/primer	0.04 - 0.05	l/m <sup>2</sup>

Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.

**Coating build-up**

- 1) Substrate preparation
- 2) Hydrophobic impregnation of StoCryl GW 100
- 3) Coating of StoCryl V 100 or StoCryl V 200

**Application** dilute with water in the ratio 1 : 4 parts by weight

- 1) Substrate preparation
- 2) Hydrophobic impregnation

Once substrate preparation is complete, apply StoCryl GW 100 by flooding, i.e. by applying a surplus. A reflective flow curtain should form on vertical surfaces; the material on horizontal surfaces should remain reflective for approx. 5 seconds.

Depending on the absorption capacity of the substrate, apply one or two layers. Leave a maximum of 4 hours of waiting time between the two application cycles. Apply the product uniformly by brush or spraying.

Consumption: approx. 0.2 - 0.25 l/m<sup>2</sup> per application cycle

- 3) Coating vertical areas  
Carry out coating work with StoCryl V 100 in accordance with the Technical Data Sheet.

# Technical Data Sheet

## StoCryl GW 100

Can be finished in-situ by overcoating with StoCryl V 100:  
 at +8°C after approx. 12 hours  
 at +20 °C after approx. 8 hours  
 at +30°C after approx. 4 hours

**Cleaning the tools** Clean with water immediately after use; hardened material can only be removed mechanically.

**Notes, recommendations, special information, miscellaneous** The Declaration(s) of Conformity can be obtained from the StoCretec Technisches InfoCenter  
 For general application notes, see [www.stocretec.de](http://www.stocretec.de) (Products) and in the latest issue of the "Technical Data Sheets" manual, in the appendix.

The minimum material consumption is defined by the tested system!

### Delivery

**Packaging** Can

Article number	Name	Container
00874-012	StoCryl GW 100	3 l can

### Storage

**Storage conditions** Store in dry and frost-free conditions; avoid direct sunlight.

**Storage life** In the original container until ... (see packaging).

### Identification

**Product group** Hydrophobic impregnation

**Safety** This product is subject to compulsory labelling in accordance with the current EU regulation.  
 You will receive an EU Safety Data Sheet with your first order.  
 Please observe the information regarding the handling of the product, its storage, and disposal.

# Technical Data Sheet

---

## StoCryl GW 100

### Special notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.

Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on the Internet.

**Sto SEA Pte Ltd**  
159 Sin Ming Road  
#06-02 Amtech Building  
Singapore 575625  
Phone: +65 6453 3080  
Fax : +65 6453 3543  
[info.sg@sto.com](mailto:info.sg@sto.com)  
[www.sto-sea.com](http://www.sto-sea.com)

**Sto SEA Sdn Bhd**  
28, Jalan Rajawali 3  
Bandar Puchong Jaya,  
47170 Selangor, Malaysia  
Phone: +60 3 8080 9066  
Fax: +60 3 8080 9255  
[info.my@sto.com](mailto:info.my@sto.com)  
[www.sto-sea.com](http://www.sto-sea.com)

**Sto SEA Pte Ltd**  
3656/49-52 Green Tower, 16<sup>th</sup> Floor  
Rama IV Rd, Klongton, Klongtoei,  
10110 Bangkok, Thailand  
Phone: +66 2 1684 921 Ext. 230  
Fax: +66 2 1684 999  
[info.sg@sto.com](mailto:info.sg@sto.com)  
[www.sto-sea.com](http://www.sto-sea.com)

**StoCretec GmbH**  
Gutenbergstr. 6  
65830 Kriftel,  
Germany  
Phone: +49 6192 401 104  
Fax: +49 6192 401 105  
[info.sg@sto.com](mailto:info.sg@sto.com)  
[www.sto-sea.com](http://www.sto-sea.com)

\*Product images may differ from the actual product.