

Technical Data Sheet

StoBit TMW / TMW M

APP modified bitumen torch-on waterproofing membrane with non-woven polyester reinforcement



Characteristics		
Area of application	 StoBit TMW For roofing and re-roofing works for sloped and flat-protected roofs Waterproofing of both above and below grade structures 	
	 StoBit TMW M For roofing and re-roofing works for sloped and flat-protected roofs Suitable for waterproofing exposed surfaces 	
Properties	 Excellent protection against ingress of water and water-borne salts Quality-controlled thickness providing uniform protection Resistant to atmospheric pollutants and chemical environment Good thermal and ageing properties Polyester reinforced which enhances the tensile strength and tear resistance 	
Application method	Apply with gas torch	

Too	hni	cal	Da	4

Criteria	Standard / test specification	Value / Unit	Notes
Elongation at break – Long / Trans	EN-12311-1	30 / 30 %	
Tensile Strength at break – Long / Trans	EN-12311-1	600 / 400 N/5 cm	
Tear Resistance - Long / Trans	EN-12310-1	140 / 160 N/5 cm	
Puncture Resistance – Static / Dynamic	EN-12730	PS-3 / PD-3	
Adhesion to Concrete (torch applied)	EN-12039	< 30 N/5 cm	
Water Impermeability	EN-1928	60 kPa	
Water vapour transmission	EN-1931	20,000 μ	•
Heat stability	EN-1110	130 °C	

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

	delivery bateri, this does not affect the salitability of the product for its interface use.
Application	
Substrate Preparation	The substrate to be waterproofed must be sound, dry, load bearing and free of any irregularities.



Technical Data Sheet

StoBit TMW / TMW M

Coating Procedure	Priming Prime the surface with one coat of StoBit Primer to improve bonding between the membrane and substrate.			
	Placing Starting from the lowest point where the drainage outlet is positioned, unroll StoBit TMW / TMW M from its original packaging and placed at the correct position where it will be torched later on. The membrane is then re-rolled from each end without changing its original alignment.			
	Torch the outer layer of membrane with a gas flame torch until the membrane surface develop a sheen or glossy appearance. Also lightly heat the primed surface with torch. Pressed the membrane firmly onto the primed surface to achieve good adhesion, working from centre to the edges, avoiding air being trapped. Continue to work by slowly unrolling the membrane, torching with flame and pressing to substrate until the end of membrane. Slide laps should be from 8-10 cm, while end laps from 12-15 cm. The bitumen compound oozing out from the lightly pressed heated overlap of the membrane should be carefully levelled with a heated round trowel to form a watertight seal.			
	Note: Primer must be fully dry before torching process.			
Application Temperature	Minimum application temperature + 8 °C Maximum application temperature + 45 °C			
Delivery				
Colour	StoBit TMW - Black StoBit TMW M - Grey StoBit TMW M - Green			
Packing	StoBit TMW / TMW M is available in 1x10 meter rolls			
•	StoBit TMW 3 mm	10 mtr / roll		
	StoBit TMW 4 mm	10 mtr / roll		
	StoBit TMW M Grey 4 kg	10 mtr / roll		
	StoBit TMW M Grey 4.5 kg	10 mtr / roll		
	StoBit TMW M Green 4.5 kg	10 mtr / roll		
	StoBit TMW M Grey 5 kg	10 mtr / roll		
	StoBit TMW M Green 5 kg	10 mtr / roll		
Storage				
Storage life / conditions	The shelf life of StoBit TMW /TMW M is approximately 5 years if stored in cool dry conditions away from direct sunlight in standing position.			
Special notes				
Health & Safety	Please refer to Safety Data Sheet			
Technical Support	Please consult the local sales office for further information and any site assistance required.			



Technical Data Sheet

StoBit TMW / TMW M

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.

Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on www.sto-sea.com.

Sto SEA Pte Ltd

www.sto-sea.com

159 Sin Ming Road #06-02 Amtech Building Singapore 575625 Phone: +65 6453 3080 Fax: +65 6453 3543 info.sg@sto.com

Sto SEA Sdn Bhd

28, Jalan Rajawali 3 Bandar Puchong Jaya, 47170 Selangor, Malaysia Phone: +60 3 8080 9066 Fax: +60 3 8080 9255 info.my@sto.com www.sto-sea.com

Sto SEA Pte Ltd

3656/49-52 Green Tower, 16th Floor Rama IV Rd, Klongton, Klongtoei, 10110 Bangkok, Thailand Phone: +66 2 1684 921 Ext. 230 Fax: +66 2 1684 999 info.sg@sto.com www.sto-sea.com

StoCretec GmbH Gutenbergstr. 6

65830 Kriftel, Germany Phone: +49 6192 401 104 Fax: +49 6192 401 105 info.sg@sto.com www.sto-sea.com

*Product images may differ from the actual product.